



75 Pigdons Road, Waurm Ponds Vic 3216, Australia
Telephone: (03) 5246 4000
Email: Tony.Pierlot@csiro.au

Performance Testing Laboratory

TEST REPORT

Report Number: 16-0103c Page 1 of 1 Date: 27/4/2016

Client: Materialised Pty Ltd
Contact: Gary Price
Address: 19 Heath Rd
Blakehurst NSW 2221
Email: Gary.Price@materialised.com

Sample Reference: Soundcheck blind

Description: beige semi-transparent, stiffened acoustic fabric

Test Method: ASTM E1050-12 Standard Test Method for Impedance and Absorption of Acoustical Materials Using a Tube, Two Microphones and a digital Frequency Analysis System

Test Parameters

Mounting method: perimeter fixed; 100 mm from end wall (100 mm air gap)
Air temperature: 21.9 °C Relative humidity: 35% Barometric pressure: 102.5 kPa
Characteristic impedance of air: 416 Pa.s/m
Instrument: 34 mm and 78 mm tube diameter, sampling frequency 44.1 kHz, frequency resolution of 10 Hz, number of averages 300, Hanning windowing of 4096 points.

Results

Frequency band Hz	Absorption Coefficient				
	Sample 1	Sample 2	Sample 3	Sample 4	Mean
250	0.28	0.32	0.30	0.26	0.29
500	0.81	0.81	0.82	0.78	0.80
1000	0.76	0.76	0.76	0.76	0.76
2000	0.63	0.64	0.64	0.64	0.64
Noise Reduction Coefficient NRC	0.62	0.63	0.63	0.61	0.62

The results contained in this report apply only to the sample submitted to the laboratory. This report must not be reproduced without the written authority of the laboratory and then shall only be reproduced in full.

Approved by: Stuart Lucas - Research Operations Manager