

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Materialised Pty Ltd
19 Heath Road
Blakehurst NSW 2221

Test Number : 17-006850
Issue Date : 7/12/2017
Print Date : 7/12/2017
Order Number : 37171

Sample Description Clients Ref : "Duos"
Block-out Drapery
Colour : Beige
End Use : Drapery
Nominal Composition : 100% Polyester with backcoating
Nominal Mass per Unit Area/Density : 420g/m2

AS 1530.2-1993

**Methods for Fire Tests on Building Materials, Components and Structures.
Part 2: Test for Flammability of Materials**

Date Tested	06/12/2017	
Flammability Index	3	
	Length	Width
Spread Factor	2	2
Heat Factor	1	1
Maximum height (d)		
Mean	3.9	4.1
Coefficient of Variation	25.7	19.6 %
Heat (a)		
Mean	2.0	2.9 °C.min
Coefficient of Variation	37.4	16.9 %
Number of Specimens Tested	9	6
Observation	Visible smoke and melting	

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

113743

24302

Page 1 of 1

© Australian Wool testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025
- Chemical Testing
- Mechanical Testing
985

: Accreditation No. 983
: Accreditation No.

Samples and their identifying descriptions have been provided by the client unless otherwise stated.
AWTA
Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall



APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc. (Hons)
MANAGING DIRECTOR