


Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

Client : Materialised Pty Ltd 19 Heath Road Blakehurst NSW 2221		Test Nun Issue Da Print Dat	te :	16-00155 11/04/201 12/04/201	16
		Order Nu	mber :	#32456	
Sample Description	Clients Ref : "Sound Check Blin Woven fabric Colour : Pumice	d"			
	End Use : Drapery - Acoustic Blir	nd			
		vira CS, 9% Polyester			
	Nominal Mass per Unit Area/Densit	-			
	Date Tested			08/04/2016	
	Date Tested			08/04/2016	
	Flammability Index			1	
		Length		Width	
	Spread Factor	Length 0		Width 0	
	Spread Factor Heat Factor	-			
	•	0		0	
	Heat Factor	0		0	
	Heat Factor Maximum height (d)	0 1		0 1	%
	Heat Factor Maximum height (d) Mean	0 1 2.6		0 1 1.4	%
	Heat Factor Maximum height (d) Mean Coefficient of Variation	0 1 2.6		0 1 1.4	% °C.min
	Heat Factor Maximum height (d) Mean Coefficient of Variation Heat (a)	0 1 2.6 51.4		0 1 1.4 15.9	
	Heat Factor Maximum height (d) Mean Coefficient of Variation Heat (a) Mean	0 1 2.6 51.4 3.1		0 1 1.4 15.9 2.3	°C.min

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.



SADY APPROVED SIGNATORY

MANAGING DIRECTOR