


Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

TEST REPORT

| Client : Materialised 19 Heath Ro Blakehurst N | bad | | Test Number Issue Date Print Date Order Numbe | : 19/07/20 ⁻ : 19/07/201 | 18 |
|--|---|-------------------------------|--|--|--------|
| Sample Description | Clients Ref : "Blockout Drap Coated woven fabric Colour : Grey End Use : Drapery Nominal Composition : Polyo Nominal Mass per Unit Area/De | ester face acrylic/silicon Ba | acking | | |
| 5 1530.2-1993 | Methods for Fire Tests on Buil Part 2: Test for Flammability o | | nts and Structu | ires. | |
| | Date Tested | | | 19/07/2018 | |
| | Flammability Index | | | 4 | |
| | | | Length | Width | |
| | Spread Factor | | 2 | 3 | |
| | Heat Factor | | 1 | 1 | |
| | Maximum height (d) | | | | |
| | Mean | | 4.1 | 4.3 | |
| | Coefficient of Variation | | 16.3 | 11.9 | % |
| | Heat (a) | | | | |
| | Mean | | 2.2 | 2.3 | °C.min |
| | Coefficient of Variation | | 12.2 | 11.1 | % |
| | Number of Specimens Tested | | 6 | 6 | |
| | Observation | Visible smoke and Melting | | | |

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.



12

APPROVED SIGNATORY

(C)