

8th August, 2012
To whom it may concern.
The attached AWTA test number 7-547637-BN has been tested using a quality which covers the following fabrics:
Vanicia Viletta Valone Vaggio.
Whilst the test has nominated Vanicia, the above patterns are one of the same and contain the same ingredients, however, simply have a different pattern embossed to create the differential.
Please do not hesitate to contact Materialised should you have any questions.
Belinda Price.

## AWTA TEXTILE TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Textile Testing A.B.N. 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT :

MATERIALISED PTY LTD

19 HEATH ROAD

BLAKEHURST NSW 2221

TEST NUMBER : 7-547637-BN

DATE

: 01/09/2006

SAMPLE DESCRIPTION

Clients Ref: "Vanicia" Coated upholstery fabric Approx thickness: 1-2mm

#### THESE RESULTS MUST BE CONSIDERED IN CONJUNCTION WITH THE COMMENTS ON THE FOLLOWING PAGE(S)

Material Specification provided by client: Nominal composition: 100% PVC face, 100% polyester back Approx mass: 490g/m2

AS/NZS

1530.3 - 1999

Simultaneous determination of Ignitability, Flame Propagation, Heat Release and Smoke Release

RESULTS:

Face tested: PVC face

	Mean		Standard	Error
Ignition time	8.00	min	0.16	
Flame propagation time	Nil	S	Nil	
Heat release integral	38.7	kJ/m2	4.3	
Smoke release, log d	-0.3740	)	0.048	7
Optical density, d	0.4358	3 /m		

Number of specimens ignited: 6

Number of specimens tested: 6

Tanitahilitar Indoar REGULATORY INDICES:

ignicability index	14	Range 0-20
Spread of Flame Index	0	Range 0-10
Heat Evolved Index	1	Range 0-10
Smoke Developed Index	6	Range 0-10

#### Comments:

These results only apply to the specimen mounted, as described in this report.

The results of this fire test may be used to directly assess fire hazard, but it should be recognized that a single test method will not provide a full assessment of fire hazard under all fire conditions. 155697 (CONTINUED NEXT PAGE) PAGE 1

© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Managing Director of AWTA Ltd.

This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 98
- Mechanical Testing of Textiles & Related Products : Accreditation No. 98

- Heat & Temperature Measurement

Accreditation No. 983 Accreditation No. 1356

The tests reported herein have been performed in accordance with its terms of accreditation. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Textile Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the

APPROVED SIGNATORY



JACKSON B.Sc.(Hons) MANAGING DIRECTOR

# AWTA TEXTILE TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Textile Testing A.B.N. 43 006 014 106 1st Floor, 191 Racecourse Road, Flemington, Victoria 3031

P.O. Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400 Fax (03) 9371 2499

## TEST REPORT

CLIENT :

MATERIALISED PTY LTD

19 HEATH ROAD

BLAKEHURST NSW 2221

TEST NUMBER : 7-547637-BN

DATE

: 01/09/2006

Each test specimen had an unattached backing of 4.5mm thick fibre reinforced cement board.

Each test specimen was restrained on the exposed face by a layer of galvanised welded square mesh made from wire of nominal diameter 0.8mm and nominal spacing 12mm in both directions and securely fixed to a backling board at four points each 100mm from the centre of the sample and the assembly clamped in four places.

To allow free movement of sample during testing all corners were folded away from the clamps.

The specimens melted and flowed away from the area of maximum heat during the test. Due to this phenomena, it should be recognised that this test result may not be a true indication of the product's fire hazard properties.

155697

PAGE 2

© Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Managing Director of AWTA Ltd.

This Laboratory is accredited by the National Association of Testing Authorities, Australia, for:
- Chemical Testing of Textiles & Related Products : Accreditation No. 98
- Mechanical Testing of Textiles & Related Products : Accreditation No. 98

amended or altered. This document, the names AWTA Textile Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved in advance by the

- Heat & Temperature Measurement

Accreditation No. 983

Accreditation No. 1356 The tests reported herein have been performed in accordance with its terms of accreditation. Samples, and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if



APPROVED SIGNATORY

JACKSON B.Sc.(Hons) MANAGING DIRECTOR