AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Materialised Pty Ltd

19 Heath Road

Blakehurst NSW 2221

Test Number : 24-000608 Issue Date : 7/03/2024

 Issue Date
 : 7/03/2024

 Print Date
 : 7/03/2024


 Order Number :
 PO 001165

Sample Description Clients Ref : "Sonic & Sun"

Woven fabric
Colour: Silver

Nominal Composition: 88% Trevira CS, 12% FR Polyester

Nominal Mass per Unit Area/Density: 186g/m2



316991 69250 Page 1 of 2

Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



IOHAFL A. JACKSON B.Sc.(Hons)

Fiona McDonald

APPROVED SIGNATORY



Australian Wool Testing Authority Ltd - trading as AWTA Product Testing A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031 P.O Box 240, North Melbourne, Victoria 3051 Phone (03) 9371 2400

TEST REPORT

Client: Materialised Pty Ltd Test Number: 24-000608

 19 Heath Road
 Issue Date
 : 7/03/2024

 Blakehurst NSW 2221
 Print Date
 : 7/03/2024

Order Number: PO 001165

AS 1530.2-1993 Methods for Fi

Methods for Fire Tests on Building Materials, Components and Structures.

Part 2: Test for Flammability of Materials

Date Tested		07-03-2024	
Flammability Index		1	
	Length	Width	
Spread Factor	0	0	
Heat Factor	1	1	
Maximum height (d)			
Mean	1.5	1.5	
Coefficient of Variation	0.0	0.0	%
Heat (a)			
Mean	1.5	1.5	°C.min
Coefficient of Variation	0.0	0.0	%
Number of Specimens Tested	6	6	

Melting,no dripping

These test results relate only to the behaviour of the test specimens of the material under the particular conditions of the test, and they are not intended to be the sole criterion for assessing the potential fire hazard of the material in use.

316991 69250 Page 2 of 2


Australian Wool Testing Authority Ltd Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.





Fiona McDonald

APPROVED SIGNATORY